

## STAINLESS STEEL GRADES

STAINLESS STEEL - GRADES CHART					
EN / W.Nr.	DIN	AISI	SS	JUS	Ž. Ravne
1.4005	X12 CrS 13	416	2380		
1.4006	X12 Cr 13	410	2302	Č41701	
1.4016	X6 Cr 17	430	2320	Č4174	
1.4021	X20 Cr 13	420	2303	Č4172	PK 3
1.4024	X15 Cr 13	420 (SAE)		Č4171	PK 2
1.4028	X30 Cr 13	420F	2304	Č4173	
1.4034	X46 Cr 13		(2304)	Č4175	
1.4057	X17 CrNi 16-2	431	2321	Č4570	PK 2 SP
1.4104	X14 CrMoS 17	430 F	2383	Č4790	
1.4112	X90 CrMoV 18	440 B		Č4772	
1.4122	X39 CrMo 17-1				
1.4301	X5 CrNi 18-10	304	2332	Č4580	PK 11 EX
1.4305	X8 CrNiS 18-9	303	2346	Č4590	
1.4306	X2 CrNi 19-11	304 L	2352	Č45701	
1.4307	X2 CrNi 18-9	304 L	2352		
1.4310	X 10 CrNi 18-8	301	2331	Č4571	
1.4362	X2 CrNiN 23-4	S 32304 (SAF)	2327		
1.4401	X5 CrNiMo 17-12-2	316	2347	Č4573	PK 12
1.4404	X2 CrNiMo 17-12-2	316 L	2348	Č45703	
1.4410	X2 CrNiMoN 25-7-4	S 32750 (SAF)	2328		
1.4432	X2 CrNiMo 17-12-3	316 L	2353		
1.4435	X2 CrNiMo 18-14-3	316 L	2353	Č45704	
1.4436	X3 CrNiMo 17-13-3	316	2343	Č45706	
1.4438	X2 CrNiMo 18-15-4	317 L	2367	Č45705	
1.4439	X2 CrNiMoN 17-13-5	(317 LMN)		Č47702	
1.4449	X5 CrNiMo 17-13	317			
1.4460	X3 CrNiMoN 27-5-2	329	2324		
1.4462	X2 CrNiMoN 22-5-3	S 32205	2377		
1.4529	X1 NiCrMoCuN 25-20-7				
1.4539	X1 NiCrMoCu 25-20-5	(904 L)	2562		
1.4541	X6 CrNiTi 18-10	321	2337	Č4572	PK 11 SP
1.4547	X1 CrNiMoCuN 20-18-7	S 31254 (SMO)	2378		
1.4550	X6 CrNiNb 18-10	347	2338	Č4582	PK 11 NB
1.4563	X1 NiCrMoCu 31-27-4		2584		
1.4571	X6 CrNiMoTi 17-12-2	316 Ti	2350	Č4574	PK 12 SP
1.4652	X1 CrNiMoMnN 24-22-8	S 32654 (SMO)			
1.4724	X10 CrAlSi 13			Č4972	PK 924
1.4742	X10 CrAlSi 18			Č4973	PK 925
1.4749	X18 CrN 28	446-1	2322		
1.4762	X10 CrAlSi 25	(446)	(2320)	Č4970	PK 10
1.4821	X15 CrNiSi 25-4			Č4586	
1.4828	X15 CrNiSi 20-12	309		Č4577	
1.4841	X15 CrNiSi 25-21	314		Č4578	PK 19
1.4835*	X9 CrNiSiN 21-11-2	S 30815	2368	* 253 MA Outokumpu trade mark	
1.4845	X8 CrNi 25-21	310 S	2361		
1.4864	X12 NiCrSi 35-16	330		Č4579	PK 20